

Quality
According to standards
Number

X37CrMoV5-1
EN ISO 4957 : 2002
1.2343



Chemical composition

C%	Si%	Mn%	P%	S%	Cr%
max 0.33-0.41	0.80-1.20	0.25-0.50	max 0.030	max 0.020	max 4.80-5.50
	Mo%	Ni%	V%		
	max 1.10-1.50	max -	max 0.30-0.50		

Temperature ▲°C

Hot-forming

1050-900

Quenching

heating up to 800,
pause, then 1000-
1040
oil, polymer, s.b. (HRC
~ 54)

Tempering

immediately
after
quenching
minimum 2
cycles

Stress-relieving

50° Under the
temperature of
tempering

Soft annealing

800-810 furnace cooling max 25°/h
to 600, then air
(HB max 229)

Mechanical properties

Tempering table after quenching at 1020°C in oil. Values on test \varnothing 20 mm

HB	543	525	518	512	512	518
HRC	54	53	52.5	52	52	52.5
R N/mm²	2010	1950	1915	1880	1880	1880
Tempering at °C	50	100	150	200	250	300
Kv +20 °C J	16	16	16	18	20	20
Thermal Expansion	10 ⁻⁶ . K ⁻¹		12.2	12.5	12.9	13
Modulus of elasticity long.	GP a	215		183	176	165
Modulus of elasticity tang.	GP a	82		70	68	63
R Hardened and tempered	N/mm ²	1600	1400	1300	1100	800
Rp 0.2	N/mm ²	1450	1200	1100	900	600
R Hardened and tempered	N/mm ²	1200	1120	1000	850	580
Rp 0.2	N/mm ²	1060	900	800	650	420
Specific heat capacity	J/(kg.K)	460			550	590
Thermal conductivity	W/(m.K)	25			28.5	29.3
Density	kg/dm ³	7.8			7.64	7.60
Specific electric resistivity	ohm.mm ² /m	0.52			0.86	0.96
Electrical conductivity	Siemens.m/mm ²	1.92			1.16	1.04
°C		20	300	400	500	600